QC ABSTRACT

NAME OF WORK: Construction of Rooms and other Civil Works at Ambedkar Bhavana (Balance Portion) in Mallasandra Colony Ward No 13 Shettyhalli Sub Division

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	Block(400*150*200)	BLOCK DENSITY	One Test		1	1
		WATER ABSORPTION	One Test		1	1
		DIMENSION ANALYSIS	One Test		1	1
		COMPRESSIVE STRENGTH	One Test		1	1
7	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1

AE WDG

8	Precast (250mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
9	PCC(M15)	Compressive Strength(7days and 28days)	2 set /6-15 cum	10.14	4	4
10	RCC(M20)	Compressive Strength(7days and 28days)	2 set /6-15 cum	10.43	4	4
11	RCC (M20)	Compressive Strength(7days and 28days)	2 set /6-15 cum	13.68	4	4
12	Column Concrete (M25)	Compressive Strength(7days and 28days)	2 set /6-15 cum	6.74	4	4
13	Lintel Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	2.79	2	2
14	Staircase Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	1.81	2	2
15	FF Roof Concrete (M25)	Compressive Strength(7days and 28days)	4 set /31-50 cum	37.21	8	8
16	Head Room Roof Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	3.9	2	2
18	Premix Carpet	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Water Absorption	One Test		1	1
		Marshal Stability	One Test		1	1
		Marshal flow	One Test		1	1
		Percent air Voids	One Test		1	1
		Percent Voids in mineral Aggregate	One Test		1	1
		Percent Voids filled with Bitumen	One Test		1	1
		Density	One Test		1	1
		Stripping Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
19	Mortar Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		Compacted Bulk Density	One Test		1	1
		Loose Bulk Density	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1
20	Plaster Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-05-11-13** **Date: 15-01-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-01-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	13-01-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.54	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.2	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.0%	Not specified
5	Initial Setting time	160 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by the Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-05-11-13** **Date: 10-02-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-01-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	13-01-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	59.0N/mm^2	Not less than 53 N/mm^2

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-05-11-13** **Date: 15-01-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	13-01-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-01-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	187	187	1.2	98.8	90-100
3	20 mm	7276	7463	49.8	50.2	30-70
4	10 mm	4074	11537	76.9	23.1	10-35
5	4.75 mm	3000	14537	96.9	3.1	0-5
6	Pan	463	15000	100.0	0	---

CIVIL PRO Sig..... Date.....

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-05-11-13** **Date: 15-01-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.8	
3	Specific Gravity	2.68	_
4	Bulk Density(Loose) (Kg/l)	1.53	_
5	Bulk Density(Compacted) (Kg/l)	1.57	_
6	Water Absorption(%)	0.23	_

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-05-11-13** **Date: 15-01-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-01-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-01-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	236	236	4.7	95.3	90-100
3	10 mm	2629	2865	57.3	42.7	25-55
4	4.75 mm	1779	4644	92.9	7.1	0-10
5	Pan	356	5000	100	0	_

CIVIL PRO Sig. Date. BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-05-11-13** **Date: 15-01-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	9.3	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.7	
3	Specific Gravity	2.67	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	24.5	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-05-11-13** **Date: 15-01-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-01-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 12-01-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	206	527	52.7	47.3	15-34	35-59	60-79	80-100
6	300 micron	205	732	73.2	26.8	5-20	8-30	12-40	15-50
7	150 micron	191	923	92.3	7.7	0-10	0-10	0-10	0-15
8	Pan	77	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO Sig. Date BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-05-11-13** **Date: 15-01-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID : **CP-2020-05-11-13** **Date: 17-01-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-01-20

Sample Type : Sunvik

Reference to BIS codes : IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.

Date of test: : 16-01-20

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2020-05-11-13** **Date: 02-03-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	25-02-20
Sample Type /Size	:	Precast Cover Slab (100mm)
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	25/02/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	2.116	4477	80.9	18.1	16.8	21.0
2	Cover Slab-2	75.49	100.52	2.122	4475	82.3	18.4	17.1	21.4
3	Cover Slab-3	75.50	100.51	2.118	4476	81.5	18.2	16.9	21.2

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : **CP-2020-05-11-13** **Date: 02-03-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 25-02-20

Sample Type /Size : Precast Cover Slab (250mm)

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 25/02/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	200.51	250.48	3.116	31570	240.9	7.6	7.1	8.9
2	Cover Slab-2	200.49	250.52	3.122	31564	242.3	7.7	7.1	8.9
3	Cover Slab-3	200.50	250.51	3.118	31567	241.5	7.7	7.1	8.9

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 23/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	23/01/2020	149.90 X 150.69 X 149.24	22588	**8.548**	406.8	18.0	18.3
2	PCC	M15	16/01/2020	23/01/2020	149.15 X 149.16 X 149.01	22247	**8.746**	418.8	18.8	
3	PCC	M15	16/01/2020	23/01/2020	150.75 X 149.29 X 150.61	22505	**8.771**	405.6	18.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 13/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	13/02/2020	149.26 X 149.40 X 149.69	22300	**8.569**	518.4	23.2	22.8
2	PCC	M15	16/01/2020	13/02/2020	151.03 X 149.67 X 149.77	22605	**8.927**	500.5	22.1	
3	PCC	M15	16/01/2020	13/02/2020	150.95 X 151.71 X 151.74	22900	**8.096**	527.6	23.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 23/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	23/01/2020	150.19 X 149.42 X 149.02	22441	**8.548**	406.9	18.1	18.2
2	PCC	M15	16/01/2020	23/01/2020	149.35 X 150.86 X 149.06	22530	**8.746**	413.4	18.4	
3	PCC	M15	16/01/2020	23/01/2020	151.92 X 150.43 X 150.19	22852	**8.771**	414.7	18.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 13/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	13/02/2020	150.10 X 151.33 X 150.73	22714	**8.569**	527.3	23.2	23.3
2	PCC	M15	16/01/2020	13/02/2020	151.04 X 150.98 X 151.59	22804	**8.927**	521.5	22.9	
3	PCC	M15	16/01/2020	13/02/2020	151.76 X 150.50 X 150.07	22840	**8.096**	547.0	23.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 23/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	23/01/2020	151.67 X 149.49 X 151.44	22672	**8.548**	426.4	18.8	18.3
2	PCC	M15	16/01/2020	23/01/2020	150.44 X 150.74 X 149.23	22678	**8.746**	411.7	18.2	
3	PCC	M15	16/01/2020	23/01/2020	150.93 X 149.43 X 149.36	22553	**8.771**	406.4	18.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 13/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	13/02/2020	150.23 X 151.91 X 151.88	22822	**8.569**	526.2	23.1	23.1
2	PCC	M15	16/01/2020	13/02/2020	149.01 X 151.97 X 149.23	22645	**8.927**	506.5	22.4	
3	PCC	M15	16/01/2020	13/02/2020	150.88 X 149.23 X 149.45	22516	**8.096**	537.9	23.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 23/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	23/01/2020	150.23 X 149.87 X 150.01	22514	**8.548**	426.5	18.9	18.8
2	PCC	M15	16/01/2020	23/01/2020	151.23 X 151.87 X 150.36	22968	**8.746**	432.6	18.8	
3	PCC	M15	16/01/2020	23/01/2020	151.05 X 149.89 X 149.90	22640	**8.771**	419.5	18.5	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 13/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-01-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	16/01/2020	13/02/2020	150.80 X 150.65 X 150.89	22718	**8.569**	524.2	23.1	23.0
2	PCC	M15	16/01/2020	13/02/2020	149.97 X 151.21 X 149.22	22677	**8.927**	507.2	22.4	
3	PCC	M15	16/01/2020	13/02/2020	151.57 X 149.85 X 150.47	22712	**8.096**	538.3	23.7	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	150.95 X 151.01 X 150.53	22795	**8.888**	583.0	25.6	25.3
2	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.72 X 151.45 X 151.71	22676	**8.602**	593.8	26.2	
3	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.41 X 151.19 X 151.00	22589	**8.770**	547.8	24.3	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 15/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	150.08 X 150.49 X 150.68	22585	**8.305**	750.8	33.2	32.9
2	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	149.10 X 149.10 X 150.20	22231	**8.026**	717.2	32.3	
3	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.61 X 149.24 X 149.68	22627	**8.902**	747.8	33.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.32 X 151.63 X 151.15	22641	**8.888**	581.3	25.7	25.6
2	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	151.50 X 150.97 X 151.78	22871	**8.602**	599.5	26.2	
3	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	151.45 X 151.20 X 151.75	22899	**8.770**	570.0	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 15/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	149.69 X 150.70 X 149.51	22559	**8.305**	746.5	33.1	33.2
2	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.89 X 150.75 X 151.04	22898	**8.026**	742.9	32.4	
3	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	149.02 X 150.44 X 149.67	22419	**8.902**	760.9	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	151.43 X 151.91 X 150.46	23004	**8.888**	588.0	25.6	25.8
2	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.02 X 149.60 X 151.32	22294	**8.602**	601.2	27.0	
3	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	150.65 X 150.33 X 151.08	22648	**8.770**	565.9	25.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 15/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	150.45 X 149.95 X 151.04	22560	**8.305**	746.2	33.1	33.1
2	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.91 X 149.56 X 149.31	22720	**8.026**	749.6	33.0	
3	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.19 X 150.70 X 150.05	22784	**8.902**	758.7	33.3	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	151.60 X 150.93 X 149.52	22882	**8.888**	589.9	25.8	25.5
2	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	150.98 X 150.42 X 151.64	22710	**8.602**	604.4	26.6	
3	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	151.77 X 150.93 X 149.00	22907	**8.770**	551.7	24.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 15/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	150.82 X 151.94 X 151.89	22916	**8.305**	767.5	33.5	33.1
2	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.10 X 150.17 X 149.19	22692	**8.026**	734.0	32.3	
3	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	150.98 X 149.77 X 149.18	22613	**8.902**	757.7	33.5	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.30 X 149.88 X 151.88	22377	**8.888**	560.1	25.0	25.4
2	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	150.37 X 149.10 X 149.75	22420	**8.602**	594.4	26.5	
3	Drain Bottom Slab Concrete	M30	18/01/2020	25/01/2020	149.28 X 150.30 X 150.67	22436	**8.770**	550.2	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 15/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-01-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.89 X 151.92 X 149.25	23074	**8.305**	777.8	33.7	33.4
2	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	150.28 X 149.38 X 149.86	22448	**8.026**	728.4	32.4	
3	Drain Bottom Slab Concrete	M30	18/01/2020	15/02/2020	151.36 X 150.58 X 149.84	22792	**8.902**	773.9	34.0	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 29/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.32 X 149.91 X 150.71	22534	**8.679**	570.7	25.3	25.7
2	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.62 X 150.26 X 151.06	22632	**8.402**	610.3	27.0	
3	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	149.16 X 149.75 X 150.01	22338	**8.232**	552.0	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 19/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	149.89 X 149.24 X 151.95	22370	**8.836**	744.3	33.3	33.0
2	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	150.38 X 150.73 X 151.89	22667	**8.255**	731.7	32.3	
3	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	150.10 X 149.96 X 150.19	22510	**8.277**	751.4	33.4	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 29/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	151.07 X 151.68 X 151.79	22915	**8.679**	586.8	25.6	25.6
2	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	151.67 X 150.83 X 151.77	22876	**8.402**	613.2	26.8	
3	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.81 X 151.69 X 151.88	22877	**8.232**	557.2	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 19/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	151.61 X 150.96 X 149.98	22887	**8.836**	761.7	33.3	33.2
2	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	149.18 X 150.36 X 151.49	22431	**8.255**	731.0	32.6	
3	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	151.76 X 149.41 X 150.46	22674	**8.277**	765.0	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 29/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.10 X 149.08 X 150.13	22376	**8.679**	573.6	25.6	25.8
2	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	149.97 X 150.26 X 151.26	22533	**8.402**	606.2	26.9	
3	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	149.80 X 149.52 X 151.45	22399	**8.232**	554.8	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 19/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	150.67 X 149.98 X 150.56	22597	**8.836**	756.4	33.5	33.2
2	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	150.56 X 150.91 X 151.36	22721	**8.255**	744.4	32.8	
3	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	149.94 X 150.88 X 150.06	22622	**8.277**	751.7	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 29/01/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.49 X 150.72 X 150.29	22682	**8.679**	569.2	25.1	25.6
2	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.79 X 149.29 X 149.93	22513	**8.402**	606.3	26.9	
3	Drain Side Wall Concrete	M30	22/01/2020	29/01/2020	150.63 X 151.35 X 150.17	22797	**8.232**	567.7	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 19/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	149.78 X 150.03 X 151.22	22471	**8.836**	748.2	33.3	33.1
2	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	150.50 X 150.57 X 151.06	22660	**8.255**	743.8	32.8	
3	Drain Side Wall Concrete	M30	22/01/2020	19/02/2020	151.25 X 149.21 X 149.73	22568	**8.277**	747.7	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 01/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	149.68 X 149.75 X 150.05	22414	**8.679**	564.3	25.2	25.3
2	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	149.66 X 150.23 X 149.34	22483	**8.402**	594.0	26.4	
3	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	149.69 X 151.46 X 151.67	22671	**8.232**	551.6	24.3	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 22/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	149.24 X 150.26 X 149.72	22424	**8.836**	752.9	33.6	33.1
2	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	150.26 X 150.34 X 150.61	22590	**8.255**	726.7	32.2	
3	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	151.98 X 151.58 X 150.41	23036	**8.277**	773.3	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 01/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	150.97 X 151.22 X 150.50	22830	**8.679**	585.7	25.7	25.5
2	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	150.89 X 151.20 X 151.10	22814	**8.402**	596.5	26.1	
3	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	150.30 X 150.17 X 150.47	22571	**8.232**	557.5	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 22/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	149.06 X 149.60 X 150.84	22300	**8.836**	747.8	33.5	33.4
2	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	150.49 X 151.44 X 149.65	22790	**8.255**	745.5	32.7	
3	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	150.85 X 151.33 X 151.07	22829	**8.277**	775.0	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 01/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	150.98 X 149.12 X 150.90	22514	**8.679**	575.7	25.6	25.4
2	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	150.59 X 149.17 X 149.60	22464	**8.402**	598.9	26.7	
3	Drain Side Wall Concrete	M30	25/01/2020	01/02/2020	151.72 X 150.76 X 151.51	22874	**8.232**	550.7	24.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 22/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-01-20

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	149.17 X 149.27 X 151.19	22267	**8.836**	745.1	33.5	32.9
2	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	150.55 X 149.84 X 149.07	22559	**8.255**	724.8	32.1	
3	Drain Side Wall Concrete	M30	25/01/2020	22/02/2020	151.48 X 149.41 X 151.86	22632	**8.277**	749.3	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 10/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-03-20

Customer ID : Culvet Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	151.16 X 150.46 X 150.57	22743	**8.679**	578.0	25.4	25.5
2	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	150.64 X 150.89 X 150.35	22731	**8.402**	601.8	26.5	
3	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	151.45 X 149.78 X 150.03	22683	**8.232**	560.7	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 31/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-03-20

Customer ID : Culvet Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	149.84 X 151.66 X 151.97	22726	**8.836**	758.5	33.4	33.1
2	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	149.80 X 149.86 X 149.31	22449	**8.255**	738.3	32.9	
3	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	149.86 X 149.50 X 151.27	22404	**8.277**	742.5	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 10/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-03-20

Customer ID : Culvet Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	151.70 X 149.38 X 150.59	22661	**8.679**	580.0	25.6	25.6
2	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	151.11 X 150.83 X 149.66	22792	**8.402**	611.9	26.8	
3	Culvet Bottom Slab Concrete	M30	03/03/2020	10/03/2020	149.37 X 151.15 X 151.53	22576	**8.232**	552.4	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 31/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-03-20

Customer ID : Culvet Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	151.72 X 149.64 X 149.75	22703	**8.836**	764.5	33.7	33.4
2	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	150.12 X 151.65 X 150.17	22766	**8.255**	751.0	33.0	
3	Culvet Bottom Slab Concrete	M30	03/03/2020	31/03/2020	151.14 X 151.41 X 150.38	22885	**8.277**	769.2	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 14/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-03-20

Customer ID : Culvert Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Side Wall Concrete	M30	07/03/2020	14/03/2020	151.62 X 149.73 X 150.03	22702	**8.679**	578.1	25.5	25.7
2	Culvert Side Wall Concrete	M30	07/03/2020	14/03/2020	150.34 X 151.63 X 149.26	22796	**8.402**	610.9	26.8	
3	Culvert Side Wall Concrete	M30	07/03/2020	14/03/2020	151.21 X 150.89 X 149.02	22816	**8.232**	567.1	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 04/04/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-03-20

Customer ID : Culvert Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Side Wall Concrete	M30	07/03/2020	04/04/2020	151.95 X 150.76 X 149.69	22908	**8.836**	757.3	33.1	33.0
2	Culvert Side Wall Concrete	M30	07/03/2020	04/04/2020	149.87 X 151.84 X 151.74	22757	**8.255**	730.0	32.1	
3	Culvert Side Wall Concrete	M30	07/03/2020	04/04/2020	149.92 X 149.17 X 151.96	22363	**8.277**	757.7	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 18/03/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-03-20

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	11/03/2020	18/03/2020	151.62 X 151.59 X 151.38	22984	**8.679**	579.8	25.2	
2	Cement Concrete Pavement	M30	11/03/2020	18/03/2020	149.09 X 151.18 X 150.11	22539	**8.402**	590.4	26.2	25.3
3	Cement Concrete Pavement	M30	11/03/2020	18/03/2020	150.54 X 149.52 X 151.14	22509	**8.232**	552.1	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 08/04/2020

Lab ID	:	**CP-2020-05-11-13**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura
Agency	:	Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/188/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-03-20
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	08/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	11/03/2020	08/04/2020	151.91 X 151.22 X 150.92	22972	**8.836**	761.3	33.1	33.2
2	Cement Concrete Pavement	M30	11/03/2020	08/04/2020	149.32 X 149.50 X 149.97	22324	**8.255**	732.2	32.8	
3	Cement Concrete Pavement	M30	11/03/2020	08/04/2020	150.99 X 149.53 X 150.73	22576	**8.277**	759.0	33.6	

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 04/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-01-20

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	28/01/2020	04/02/2020	151.75 X 151.80 X 150.55	23036	**8.983**	417.6	18.1	18.6
2	RCC	M20	28/01/2020	04/02/2020	149.66 X 151.97 X 150.99	22743	**8.907**	427.3	18.8	
3	RCC	M20	28/01/2020	04/02/2020	149.64 X 149.17 X 151.05	22322	**8.633**	421.3	18.9	

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certifi

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-05-11-13** **Date: 25/02/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads Drains and Other Development Works in Thindlu Colony Main Roads Cross Roads and Surrounding Area in Ward No 9 Vidyaranyapura

Agency : Executive Engineer, Karnataka Rural Infrastructture Development Limitd, #280, 59th Cross Road , 17th C Main Road , 3rd Y Block , Rajajinagar, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/188/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-01-20

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/02/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	28/01/2020	25/02/2020	150.91 X 151.33 X 151.17	22837	**8.206**	534.3	23.4	23.1
2	RCC	M20	28/01/2020	25/02/2020	151.53 X 150.26 X 150.38	22768	**8.123**	510.3	22.4	
3	RCC	M20	28/01/2020	25/02/2020	151.96 X 149.36 X 149.91	22696	**8.260**	535.2	23.6	

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****